

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
11 August 2005 (11.08.2005)

PCT

(10) International Publication Number
WO 2005/073301 A1

(51) International Patent Classification⁷: **C08J 9/16**

(21) International Application Number:
PCT/KR2004/000182

(22) International Filing Date: 30 January 2004 (30.01.2004)

(25) Filing Language: Korean

(26) Publication Language: English

(71) Applicant and

(72) Inventor: **PARK, Bong-Kuk** [KR/KR]; 102-905 Gyeyang
Woobang APT 595(32/6), Sa-Dong, Gyeongsan-Si,
Gyeongbut 712-190 (KR).

(74) Agent: **KIM, Kyung-Mi**; 1217-5 Jang-gi B/D, 4F, Bonri-
dong, Dalseo-gu, Kisan International Patent & Law Office,
Dae-gu 704-120 (KR).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.


(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: EXPANDED POLYSTYRENE BEAD HAVING FUNCTIONAL SKIN LAYER, MANUFACTURING PROCESS THEREOF, AND FUNCTIONAL EPS PRODUCT AND MANUFACTURING PROCESS THEREOF USING THE SAME



(57) Abstract: Disclosed herein are expanded polystyrene particles having a polyvinyl acetate resin-based functional skin layer formed on the surface of expanded polystyrene particles. Further disclosed are a process for producing the expanded polystyrene particles and the use of the expanded polystyrene particles. According to the expanded polystyrene particles of the present invention, inherent properties of the expanded polystyrene, e.g., light weight, thermal insulation properties, shape stability, buffering properties and sound absorption, are ensured, and superior low-temperature bonding properties, air-tightness, waterproofness and durability are provided by the vinyl acetate based polymer constituting the skin layer. Optionally, various functional additives, including flame retardants, water repellents, antibacterial agents, colorants, flavoring agents, etc., can be added to the polyvinyl acetate resin to impart a variety of functions to the expanded polystyrene particles in a simple manner.

WO 2005/073301 A1

BEST AVAILABLE COPY

EXPANDED POLYSTYRENE BEAD HAVING FUNCTIONAL SKIN LAYER, MANUFACTURING PROCESS THEREOF, AND FUNCTIONAL EPS PRODUCT AND MANUFACTURING PROCESS THEREOF USING THE SAME

5

Technical Field

10 The present invention relates to expanded polystyrene molded products having various functions, including flame-retardation, antibacterial properties, coloration properties, etc. More particularly, the present invention relates to (pre-) expanded polystyrene particles having a functional skin layer produced by coating the surface of (pre-) expanded polystyrene particles with a functional coating composition, a process for producing the expanded polystyrene particles, functional
15 expanded polystyrene molded products manufactured using the expanded polystyrene particles with a functional skin layer, and a process for manufacturing the polystyrene molded products.

20

Background Art

Expanded polystyrene is a polymer resin obtained by heating and curing the expandable polystyrene resin including expanding agent, such as pentane (C_5H_{12}) or butane (C_4H_{10}) in polystyrene resin or its copolymer resins, to generate foams
25 therein. Expanded polystyrene is white in color, light in weight, and is superior in water resistance, thermal insulation properties, sound absorption and buffering properties. Due to these advantages, expanded polystyrene resin is widely used as a packaging material, a construction material, a material for floats, life jackets, decorative articles, insulators, living products, such as food containers and
30 disposable products, and the like.

More detailed explanation regarding a molding process of expanded polystyrene products will be described below. A polystyrene or styrene copolymer resin containing an expanding agent in the shape of a bead having a diameter 0.2~0.3 mm or a pellet having a length of about 2.5 mm is pre-expanded to produce
35 expanded particles (usually in the forms of beads). Thereafter, the expanded particles are aged and dried. The aged expanded particles are placed in a mold, heated with a high-pressure steam, and thus molded into a desired shape.

The expanded polystyrene thus produced contains 98 vol% of air and only

about 2 vol% of the polymer resin. Further, the expanded polystyrene has a unique expanded structure in which air is enclosed by plastic foams. Based on this structure, since the expanded polystyrene is lightweight and shows superior buffering properties, thermal insulation properties, and sound absorption, it can be widely utilized in many applications.

However, since the expanded structure makes the expanded polystyrene more susceptible to some chemicals than the chemical resistance inherent to the polystyrene resin, the expanded structure is an obstacle in imparting a variety of functions upon the expanded polystyrene particles.

That is, the addition of functional components to expanded polystyrenes in order to impart additional functions to expanded polystyrene products presents difficulties that water resistance and heat resistance of the functional components, and moldability and chemical resistance of the expanded polystyrene must be comprehensively taken into account. Accordingly, functional expanded polystyrene molded products hitherto developed are very limited in the selection of the amount and kind of functional components within the range that does not affect physical and chemical properties during preparation of polystyrene.

Particularly, since expanded polystyrenes have relatively low melting point, and the molten polystyrene has low viscosity, molded products made of expanded polystyrene lose their structure and are melted easily by fire, thus being converted to a combustible liquid material. Under these circumstances, regulations including the Fire Services Act, in most developed countries, restrict the use of expanded polystyrenes, which prohibits the development of the expanded polystyrenes as construction materials.

In order to solve these problems, great efforts have been devoted to developing flame-retardant or fire-resistant expanded polystyrenes. For example, U.S. Patent No. 6,384,094 discloses a process for preparing a fire-resistant expandable polystyrene by adding 1~12 wt% of an expandable graphite or an expanded graphite to a suspension containing a styrene monomer. In addition, the patent publication proves the usefulness of the expandable polystyrene thus prepared.

However, the expandable graphite begins to expand at about 900°C, whereas the polystyrene leaves 3 wt% of ash behind at 500°C or above because of its extremely low heat resistance. The expandable graphite is expanded upon high-temperature heating to perform its thermal insulation, but the graphite loses its structure due to the absence of a material capable of binding the graphite, resulting in poor fire resistance.

On the other hand, Korean Utility Model No. 323680 describes a flame-retardant expanded polystyrene panel manufactured by coating an aqueous sodium silicate solution on the surface of an expanded polystyrene particle, and irradiating

microwaves to the coating to heat-bond the sodium silicate to the polystyrene. This technology has disadvantages in that the coating of the sodium silicate is poor in water resistance and expensive equipment is required for the microwave irradiation.

5

Disclosure of the Invention

Therefore, the present invention has been made in view of the above problems, and it is an object of the present invention to provide an expanded polystyrene that can be produced using conventional molding equipment without the need for additional expensive equipment and developed into various functional products superior in flame retardation, fire resistance, antibacterial properties, waterproofness, aromatic properties, coloration properties, etc.

The object of the present invention can be achieved by coating the surface of expanded polystyrene particles with a functional coating composition to form a functional skin layer inside the particles, followed by molding. The functional coating composition used herein contains at least one functional additive, and a polyvinyl acetate resin with high affinity to the expanded polystyrene particles and low-temperature melt bonding property so as to be suitable for steam molding.

In accordance with one aspect of the present invention, there are provided expanded polystyrene particles consisting of an inner expanded polystyrene layer and a functional skin layer wherein the inner expanded polystyrene layer is formed by heating and expanding expandable polystyrene beads or pellets, and the functional skin layer is formed by coating the surface of the inner expanded polystyrene layer with a functional coating composition containing 10~99 wt% of a vinyl acetate based polymer and 0.1~90 wt% of at least one functional additive.

In accordance with another aspect of the present invention, there is provided a process for producing the expanded polystyrene particles with a functional skin layer, comprising the steps of:

heating and expanding expandable polystyrene beads or pellets to produce expanded polystyrene particles;

applying a functional coating composition to the surface of the expanded polystyrene particles, the functional coating composition being prepared by mixing or dissolving at least one functional additive with a vinyl acetate based polymer solution to form a functional skin layer; and

adding a release agent to the expanded polystyrene particles whose surface is coated with the functional coating composition, to separate the expanded polystyrene particles having the functional skin layer into individual particles, and drying the separated particles.

In accordance with another aspect of the present invention, there is

provided a process for manufacturing the functional expanded polystyrene molded product comprising the steps of introducing the expanded polystyrene particles having a functional skin layer into a molder, and applying high-pressure steam to the molder to bond the expanded polystyrene particles with each other.

5 In accordance with yet another aspect of the present invention, there is provided a functional expanded polystyrene molded product made of the expanded polystyrene particles with functional skin layer according to the present invention.

10 A more detailed explanation concerning the structure of the expanded polystyrene particles having a functional skin layer according to the present invention will be given below. The expanded polystyrene particles having a functional skin layer are spherical particles having a skin-core structure wherein the overall diameter of the expanded polystyrene particles is between about 1 mm and about 30 mm, the diameter of the expanded polystyrene particles constituting the inner core layer is between about 0.999 mm and about 29.999 mm, and the thickness of the outer skin layer is between about 1 μ m and about 100 μ m. The expanded polystyrene particles constituting the core layer account for 5~99 wt%, the functional skin layer accounts for 1~95 wt%, and other residues account for 5 wt% or less, based on the total weight of the expanded polystyrene particles.

20 The expanded polystyrene particles constituting the core layer include those previously known in the art. The components and production processes are as explained in the above prior art.

On the other hand, the functional skin layer is formed by coating the surface of expanded polystyrene particles with a functional coating composition containing a vinyl acetate based polymer solution and at least one functional additive, followed by separating (to individual particles) and drying. The vinyl acetate based polymer solution is prepared by dissolving 3~80 wt% of a vinyl acetate based polymer in a solvent. The vinyl acetate based polymer can be a vinyl acetate homopolymer, or a copolymer of vinyl acetate and at least one monomer selected from: vinyl esters, such as vinyl caproate and vinyl stearate; acrylic esters, such as ethyl acrylate, butyl acrylate and octyl acrylate; fumaric acid esters, such as dibutyl maleate; carboxylic acids, such as maleic acid, acrylic acids and itaconic acid; vinyl alcohols; butadienes; and caprolactones; or a mixture or a blend thereof. The vinyl acetate based polymer has a degree of polymerization (DP) of 10~100,000. It is preferred that the content of the vinyl acetate monomer in the vinyl acetate based polymer is 55% or more.

40 Examples of suitable solvents to prepare the vinyl acetate based polymer solution include water, and organic solvents such as alcohols, esters, ketones, carboxylic acids, aromatics, and halogenated hydrocarbons. It is preferred to select a solvent having relatively high volatility and reduced human toxicity, particularly,

minimally dissolving or eroding the surface of expanded polystyrene particles. In this respect, alcohols are preferred. The concentration of the resin component is determined within the range defined above, taking into account the adhesion to the surface of the expanded polystyrene particles and workability upon handling.

5 The functional additive can be added for intended functions without particular limitations so long as it is readily dissolved or dispersed in the vinyl acetate based polymer solution and does not erode or dissolve the surface of the expanded polystyrene particles. Examples of such additives include expanding agents, nucleating agents, lubricants, antioxidants, heat stabilizers, ultraviolet
10 stabilizers, biostabilizers, fillers, reinforcing agents, plasticizers, colorants, impact-resistant agents, flame retardants, antistatic agents, cross-linking agents, fluorescent whitening agents, thermal conductivity-imparting agents, electrical conductivity-imparting agents, permeability modifiers, magnetism-imparting agents, surfactants, stabilizers, excipients, drugs, solvents, hardeners, desiccants, fortifying agents, flavoring agents, antibacterial agents, etc. These additives may be added alone or
15 in combination as a mixture of two or more agents compatible with each other.

In particular, when a flame retardant, such as antimony trioxide, a phosphoric compound, boron, boric acid or aluminum oxide, is added, a kind of fire wall surrounding the surface of the expanded polystyrene particles is built, which
20 prevents the spread of a fire to sites not directly reached by the flame and maintains the overall shape of the skin layer acting as a skeleton unchanged, leading to a very effective flame-retardant expanded polystyrene product.

The vinyl acetate based polymer solution containing the functional additive is uniformly applied to the surface of the expanded polystyrene particles. At this
25 step, if the viscosity of the polymer solution is low, it is advantageous to stir the expanded polystyrene particles while the polymer solution is sprayed on the surface of the particles. Meanwhile, if the polymer solution is highly viscous, the expanded polystyrene particles can be mixed with the polymer solution in a mixer with stirring to apply the polymer solution to the surface of the particles.

30 The application of the vinyl acetate based polymer solution containing the functional additive to the expanded polystyrene particles may cause the polystyrene particles to be agglomerated due to the viscosity of the polymer solution, which makes it difficult to manufacture a molded product from the expanded polystyrene particles. Therefore preferably, the polymer solution is uniformly applied to the
35 surface of the expanded polystyrene particles, followed by the steps of separating and drying, to produce the final expanded polystyrene particles having the functional skin layer.

As the release agent used for separating, there may be used a liquid material or a solid powder different from the solvent used to prepare the vinyl
40 acetate based polymer solution. When the solid powder is used, the moldability of

the expanded polystyrene particles is degraded and dust is created during drying. When the liquid material is too lipophilic, it is more compatible with the polystyrene than with the vinyl acetate based polymer, causing the separation of the polystyrene from vinyl acetate based polymer. Accordingly, the use of excessively lipophilic liquid materials should be avoided. Thus, preferred release agent should be more or less hydrophilic liquid type material such that it can be uniformly applied to the exterior surface of the vinyl acetate based polymer, and should remain until the solvent of the polymer solution is appropriately removed such that it can. Examples of suitable release agents include, but are not limited to, hydrophilic liquid materials, such as water, ethylene glycol and glycerin, containing two or more hydroxyl groups (-OH) in their molecular structure, and silicone oils. These release agents can be used alone or as a mixture of two or more thereof. The release agent is used in an amount of 1~40 wt% of the vinyl acetate based polymer. The amount of the release agent used is properly selected depending on the surface area of the expanded polystyrene particles and the kind of the functional coating composition constituting the skin layer.

After the release agent is uniformly added, the mixture is dried with stirring to separate the expanded polystyrene particles into individual particles. Drying is carried out in hot air at 100°C or lower with stirring. Alternatively, the drying may be carried out in a drier at 100°C or lower with stirring, or may be carried out under reduced pressure. For better workability, a combination of vacuum drying and heating is most effective.

The functional skin layer thus formed contains 10~99 wt% of the vinyl acetate based polymer, 0.1~90 wt% of the functional additive, and 20 wt% or less of residues of the solvent and the release agent. The content of the functional additives is greatly dependent on functions to be imparted. For example, flame-retardants, reinforcing agents and fillers are added in large amounts, but colorants can attain desired effects using only small amounts. Within the range defined above, the vinyl acetate based polymer can serve as a matrix capable of forming the skin layer.

The expanded polystyrene particles having the functional skin layer are stored in a silo before use. For use, the expanded polystyrene particles are taken out of the silo, placed in a mold having a desired shape, and molded using high-pressure steam to manufacture a functional expanded polystyrene molded product. This molding may be performed in accordance with the same procedure as conventional molding processes of expanded polystyrenes.

Brief Description the Drawings

The above and other objects, features and other advantages of the present

invention will be more clearly understood from the following detailed description taken in conjunction with the accompanying drawings, in which:

Fig. 1 is an electron micrograph (30x) showing a cutaway portion of the surface of an expanded polystyrene particle (C1) having a flame-retardant skin layer produced in Example 1 of the present invention;

Fig. 2 is an electron micrograph (400 x) showing an interface between a skin layer and a core layer of the cutaway portion shown in Fig. 1;

Fig. 3 is a photograph showing the initial state of a sample for a flame-retardation test, produced in Example 1 of the present invention;

Figs. 4 and 5 are front and side photographs taken after the flame-retardation test for the sample shown in Fig. 3, respectively;

Fig. 6 is a photograph showing the results of an antibacterial performance test for an expanded polystyrene molded product manufactured in Example 2 of the present invention; and

Fig. 7 is an enlarged photograph showing the cross section of an aesthetic expanded polystyrene molded product manufactured in Example 3 of the present invention.

Best Mode for Carrying Out the Invention

The present invention will now be described in more detail with reference to the following several examples of the manufacture of functional expanded polystyrene molded products.

Example 1: Manufacture of flame-retardant expanded polystyrene molded product

A. Preparation of flame-retardant polyvinyl acetate solution (A1)

450g of a polyvinyl acetate resin having a degree of polymerization of 500 was uniformly dissolved in 550g of methanol to prepare 1 kg of polyvinyl acetate solution. To the polymer solution was added 1 kg of aluminum hydroxide particles having an average particle size of 7.5 μm . The resulting mixture was uniformly dispersed to prepare 2 kg of a methanolic polyvinyl acetate solution (A1) containing the flame-retardant additive.

B. Coating on expanded polystyrene particles

Expandable polystyrene particles were expanded to an average of 80 fold, and dried. 2 kg of the expanded polystyrene particles were charged into a 200-liter ribbon mixer. 2 kg of the flame-retardant polyvinyl acetate polymer solution (A1) prepared in step A was added to the expanded polystyrene particles with stirring at 50 rpm for one minute to uniformly coat the expanded particles, yielding 4 kg of

expanded polystyrene particles whose surface was coated with the flame-retardant polyvinyl acetate polymer solution.

C. Drying, separating, and production of expanded polystyrene particles having flame-retardant skin layer

Stirring was continued for about 10 seconds while applying hot air at 60°C to the ribbon mixer. Then, 50g of ethylene glycol were sprayed with stirring to allow the expanded polystyrene particles coated with the flame-retardant polyvinyl acetate polymer solution to separate into individual particles. The separated particles were dried with stirring for 3 minutes to produce expanded polystyrene particles (C1) having a flame-retardant skin layer.

D. Production of flame-retardant expanded polystyrene molded product

The expanded polystyrene particles (C1) having a flame-retardant skin layer produced in step C were put in a steam molder for EPS, heated at a steam pressure of 0.6 kg/cm³ for 50 seconds, sustained for 10 seconds, and cooled to manufacture a flame-retardant expanded polystyrene molded product (D1) having a density of 35 kg/m³.

E. Observation of skin-core structure

For observation of the skin-core structure of the expanded polystyrene particles having a flame-retardant skin layer produced in step C, one particle (C1) of the expanded polystyrene particles was selected. A portion of the surface of the particle (C1) was cut, and then the cutaway portion was observed under an electron microscope with a magnification of 30x (see Fig. 1). This observation reveals that the expanded polystyrene particle (C1) produced in this example is a spherical particle having an expanded structure completely coated with the flame-retardant skin layer.

A higher magnification (400 x) of the interface between the skin layer and the core layer of the expanded polystyrene particle (C1) is shown in Fig. 2. As shown in Fig. 2, the skin layer was completely adhered to the inner expanded polystyrene layer.

F. Flame-retardation test

The flame-retardant expanded polystyrene molded product D1 manufactured in step D was cut into a plate-shaped sample having dimensions of 2 cm (l) x 2 cm (w) x 1 cm (h) (see Fig. 3), which was used for the flame-retardation test.

The sample was exposed to a 4 cm high flame from a Bunsen burner for 30

seconds to conduct a flame-retardation test, and the obtained results are shown in Figs. 4 and 5.

As shown in Figs. 4 and 5, only a portion of the expanded polystyrene particles exposed to the surface were collapsed by heating, but heat and flame were blocked by means of the skin layer and the skeleton of the molded product (D1) was maintained, confirming that the original structure of the molded product (D1) was unchanged.

Example 2: Manufacture of antibacterial expanded polystyrene molded product

A. Preparation of antibacterial polyvinyl acetate solution

450g of a polyvinyl acetate resin having a degree of polymerization of 500 was uniformly dissolved in 550g of methanol to prepare 1 kg of a polyvinyl acetate solution, and then 0.2 kg of ethyl paraben was added thereto. The resulting mixture was completely dissolved with stirring for one hour to prepare 1.2 kg of a methanolic polyvinyl acetate solution (A2) containing the antibacterial additive.

B. Coating on expanded polystyrene particles

2.5 kg of expanded polystyrene particles coated with the antibacterial polyvinyl acetate solution were produced in the same manner as in Example 1 (B), except that 0.5 kg of the antibacterial polyvinyl acetate solution (A2) prepared in step A was added instead of the flame-retardant polyvinyl acetate solution (A1).

C. Drying, separating, and preparation of expanded polystyrene particles having antibacterial skin layer

Drying and separating were carried out in the same manner as in Example 1 to produce expanded polystyrene particles (C2) having an antibacterial skin layer.

D. Manufacture of antibacterial expanded polystyrene molded product

The expanded polystyrene particles (C2) having an antibacterial skin layer produced in step C were charged into a steam molder for EPS, heated at a steam pressure of 0.6 kg/cm³ for 40 seconds, sustained for 10 seconds, and cooled to manufacture an antibacterial expanded polystyrene molded product (D2) having a density of 15 kg/m³.

E. Antibacterial performance Test

A portion of the antibacterial expanded polystyrene molded product D2 manufactured in step D was ground. After 0.4g of the ground molded product and a test bacterial solution in which *Staphylococcus aureus* was incubated were subjected to shaking culture at a shaking frequency of 150 cycles per minute at 35°C

for 24 hours, the number of the bacteria was counted and the bacterial decrease rate (bacteriostatic rate) was determined.

After the shaking culture, the initial bacterial concentration (1.3×10^5 count/ml) of the test bacterial solution was decreased to 10 count/ml (Fig. 6).

As apparent from the results shown in Fig 6, the antibacterial test performed by the shake-flask method confirms a bacterial decrease of 99.9% in the antibacterial expanded polystyrene molded product D2 produced in this example.

Example 3: Manufacture of aesthetic expanded polystyrene molded product

A. Preparation of colored polyvinyl acetate solution

25g of a polyvinyl acetate resin having a degree of polymerization of 500 was uniformly dissolved in 475g of methanol to prepare 0.5 kg of a polyvinyl acetate solution. 10g of a black pigment was added to the polymer solution, and was completely dissolved with stirring for one hour to prepare 0.51 kg of a methanolic black-colored polyvinyl acetate solution (A3).

B. Coating on expanded polystyrene particles

2.51 kg of expanded polystyrene particles coated with the colored polyvinyl acetate polymer solution were prepared in the same manner as in Example 1 (B), except that 0.51 kg of the colored polyvinyl acetate polymer solution (A3) prepared in step A was added instead of the flame-retardant polyvinyl acetate solution (A1).

C. Drying, separating, and production of expanded polystyrene particles having colored skin layer

Expanded polystyrene particles (C3) having a black skin layer were produced in the same manner as in Example 1 (C), except that 250g of water was used instead of ethylene glycol.

D. Manufacture of aesthetic expanded polystyrene molded product

The expanded polystyrene particles (C3) having a black skin layer produced in step C were charged into a steam molder for EPS, heated at a steam pressure of 0.6 kg/cm^3 for 40 seconds, sustained for 10 seconds, and cooled to manufacture an aesthetic expanded polystyrene molded product (D3) having a density of 15 kg/m^3 .

E. Observation of cross section of aesthetic expanded polystyrene molded product

The surface of the expanded polystyrene molded product D3 manufactured

in step D was wholly black-colored. A 5 cm deep piece was cut from the expanded polystyrene molded product D3, and then the cross section of the piece was observed under a microscope. The photograph is shown in Fig. 7.

As apparent from the photograph, the cross section of the expanded polystyrene molded product (D3) had a slightly irregular shape similar to a honeycomb wherein the black-colored skin layer was formed between the white expanded polystyrene particles.

In the case of a commercial block molding product manufactured by cutting the block-shaped molded product to a desired thickness, the size and color of the expanded polystyrene particles, and the color of the skin layer are varied, making it possible to manufacture aesthetic expandable polystyrene panels exhibiting various color effects.

Industrial Applicability

As apparent from the above description, according to the expanded polystyrene particles of the present invention, inherent properties of expanded polystyrene, e.g., light weight, thermal insulation properties, shape stability, buffering properties and sound absorption, are ensured by the expanded polystyrene particles constituting the core layer, and at the same time, superior low-temperature bonding properties, air-tightness, waterproofness and durability are provided by the low-softening point vinyl acetate based polymer constituting the skin layer.

In addition, superior adhesion of the vinyl acetate based resin to polystyrene, and relatively good low-temperature adhesion properties of the vinyl acetate based polymer enable improvement of the physical properties, e.g., compressive strength, tensile strength and flexural strength, of the molded products of the present invention. Optionally, various functional additives, including flame retardants, water repellents, antibacterial agents, colorants, flavoring agents, etc., can be added to the vinyl acetate based polymer to impart a variety of functions to the expanded polystyrene particles of the present invention in a simple manner. Therefore, the expanded polystyrene particles of the present invention can be applied to manufacture of lightweight industrial materials, particularly construction materials, with various functions.

Although the preferred embodiments of the present invention have been disclosed for illustrative purposes, those skilled in the art will appreciate that various modifications, additions and substitutions are possible, without departing from the scope and spirit of the invention as disclosed in the accompanying claims.

Claims:

1. An expanded polystyrene particle with a functional skin layer consisting of an inner expanded polystyrene layer and a functional skin layer wherein the inner expanded polystyrene layer is formed by heating and expanding an expandable polystyrene bead or pellet, and the functional skin layer is formed by coating the surface of the inner expanded polystyrene layer with a functional coating composition containing 10~99 wt% of a vinyl acetate based polymer and 0.1~90 wt% of at least one functional additive.

2. The expanded polystyrene particle with functional skin layer according to claim 1, wherein the vinyl acetate based polymer is a vinyl acetate homopolymer, or a copolymer of vinyl acetate and at least one monomer selected from: vinyl esters, such as vinyl caproate and vinyl stearate; acrylic esters, such as ethyl acrylate, butyl acrylate and octyl acrylate; fumaric acid esters, such as dibutyl maleate; carboxylic acids, such as maleic acid, acrylic acids and itaconic acid; vinyl alcohols; butadienes; and caprolactones; or a mixture or a blend thereof, and has a degree of polymerization (DP) of 10~100,000.

3. The expanded polystyrene particle with functional skin layer according to claim 1, wherein the functional skin layer has a thickness corresponding to 0.003~10% of the overall diameter of the particle, and makes up 1~95 wt% based on the total weight of the particle.

4. The expanded polystyrene particle according to claim 1, wherein the functional additive is selected from expanding agents, nucleating agents, lubricants, antioxidants, heat stabilizers, ultraviolet stabilizers, biostabilizers, fillers, reinforcing agents, plasticizers, colorants, impact-resistant agents, flame retardants, antistatic agents, crosslinking agents, fluorescent whitening agents, thermal conductivity-imparting agents, electrical conductivity-imparting agents, permeability modifiers, magnetism-imparting agents, surfactants, stabilizers, excipients, drugs, solvents, hardeners, desiccants, fortifying agents, flavoring agents, antibacterial agents, and mixtures thereof.

5. A functional expanded polystyrene molded product manufactured by molding the expanded polystyrene particle with functional skin layer according to any one of claims 1 to 4.

6. A process for producing expanded polystyrene particles with functional skin layer, comprising the steps of:

heating and expanding expandable polystyrene beads or pellets to produce expanded polystyrene particles;

5 applying a functional coating composition to the surface of the above expanded polystyrene particles, the functional coating composition being prepared by mixing or dissolving at least one functional additive with a vinyl acetate based polymer solution to form a functional skin layer; and

10 adding a release agent to the expanded polystyrene particles whose surface is coated with the functional coating composition, to separate the expanded polystyrene particles having the functional skin layer into individual particles, and drying the separated particles.

15 7. The process according to claim 6, wherein the solvent used to prepare the vinyl acetate based polymer solution is water, or an organic solvent selected from alcohols, esters, ketones, carboxylic acids, aromatics, and halogenated hydrocarbons, or mixtures thereof.

8. The process according to claim 6, wherein the vinyl acetate based polymer solution contains 3~80 wt% of a vinyl acetate based polymer.

20 9. The process according to claim 6, wherein the release agent is selected from hydrophilic liquid materials containing two or more hydroxyl groups (-OH) in their molecular structure, such as water, ethylene glycol and glycerin, and silicone oils, and mixtures thereof.

25 10. A process for manufacturing a functional expanded polystyrene molded product, comprising the steps of: introducing the expanded polystyrene particles with functional skin layer produced by the process according to any one of claims 6 to 9 into a steam molder; and applying high-pressure steam to the molder to bond the expanded polystyrene particles with functional skin layer to each other through
30 their functional skin layer, followed by cooling.

DRAWINGS

Fig 1




Fig 2



Fig 3



Fig 4




Fig 5



Fig 6





Fig 7



INTERNATIONAL SEARCH REPORT

International application No.

PCT/KR2004/000182

A. CLASSIFICATION OF SUBJECT MATTER**IPC7 C08J 9/16**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7 C08J, C08F, C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
Korean patents and applications for inventions

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 91/14724 A (E.I. Du Pont De Nemours and Company) 03 October 1991 See the whole document	1-10
A	US 5786398 A (Owens-Corning Fiberglas Tech. Inc.) 28 July 1998 See the whole document	1-10
A	JP 55-29533 A (Hitachi Ltd.) 01 March 1980 See the whole document	1-10
A	US 6384094 A (BASF Aktiengesellschaft) 07 May 2002 Cited in the application, see the whole document	1-10
A	JP 01-264979 A (Fujimori Kogyo KK) 23 October 1989 See the whole document	1-10

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

25 OCTOBER 2004 (25.10.2004)

Date of mailing of the international search report

25 OCTOBER 2004 (25.10.2004)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

SOHN, Chang Ho

Telephone No. 82-42-481-5538



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2004/000182

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 91/14724 A	03.10.1991	US5532284A AU7306691A1 EP521877A1 CN1055187A	02.07.1996 21.10.1991 13.01.1993 09.10.1991
US5786398A	28.07.1998	CA2214770A1 JP8319365A KR164685B1 US5786398A W09630437A1	03.10.1996 03.12.1996 20.03.1999 28.07.1998 03.10.1996
JP 55-29533 A	01.03.1980	none	
US6384094B1	07.05.2002	AT215582T AU5158499A BR9912446A CN1114649B CZ20010305A3 EP1102807A1 ES2176006T3 JP2002521543T NO20010445A PL345699A1 RU2223984C2 US6384094B1 W00006635A1	15.04.2002 21.02.2000 17.04.2001 16.07.2003 17.10.2001 30.05.2001 16.11.2002 16.07.2002 29.01.2001 02.01.2002 20.02.2004 07.05.2002 10.02.2000
JP 01-264979 A	23.10.1989	EP350064A2 US4984274A KR9209959B1	10.01.1990 08.01.1991 06.11.1992

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.